

PRODUCT INFORMATION

Collagen R Solution 0.2 %

Cat. No. 47254

Product description:

| | |
|--------------------|---|
| General | Collagen is the major structural component of extracellular matrices found in connective tissues and internal organs, but is most prevalent in the dermis, tendons and bones. Type I collagen is a heterodimer composed of two $\alpha_1(I)$ chains and one $\alpha_2(I)$ chain that spontaneously forms a triple helix scaffold at neutral pH and 37 °C: |
| Application | <ul style="list-style-type: none"> • Excellent substrate for the cultivation of epithelial cells and a number of other cell lines • Propagation of cells which are not able to grow on glass or plastic surfaces¹⁻² • Cell adhesion in culture media without serum or fibronectin³⁻⁴ • Experiments in cell migration⁵ • Changes in cell morphology in three dimensional collagen gels⁶⁻⁷ • Morphological studies⁸ • Preservation of differentiation status of higher cells <i>in vitro</i>⁹⁻¹⁰ • Influence of substrate and cell morphology on DNA-synthesis and cell proliferation¹¹ • Development of tissue-like structures <i>in vitro</i> and the use in wound healing processes¹² |
| Composition | 2 mg/ml acid soluble collagen (Type I) from rat tail in 0.1 % acetic acid |
| Storage | Store solution at +2 °C - +8 °C |

Preparation of collagen gels:

| | |
|-------------------------------------|--|
| Additional required material | <ul style="list-style-type: none"> • 10x medium, sterile (e.g. BME with Earle's BSS or MEM Eagle with Earle's BSS) • 0.34 M NaOH, sterile • Petri dishes (polystyrene or glass) of ca. 10 cm diameter |
| Pouring of collagen gels | <ol style="list-style-type: none"> 1. Mix 20 ml 10x medium and 10 ml 0.34 M NaOH directly before use. 2. Dispense 1.7 ml Collagen R solution. Evenly on the bottom of the culture dish (you may have to dilute it with 0.1 % acetic acid). 3. Add NaOH/medium mixture until the color of the indicator changes from yellow to slightly pink (pH 7.0 -7.5) and turn the dish in circles for 15 seconds. 4. Let the gel set at room temperature or at 37 °C. Duration 15 – 60 minutes. |

Coating of cell culture dishes with Collagen R:

Optimal conditions for attachment and growth must be determined for each cell line and application by the user.

Described is a 2 ml formulation.

| | |
|-------------------------------------|--|
| Additional required material | <ul style="list-style-type: none"> • 9.0 % NaCl solution • 0.17 M NaOH, sterile • Petri dishes (Polystyrene or glass) of ca. 10 cm diameter |
| Coating | <ol style="list-style-type: none"> 1. 0.2 ml 9.0 % NaCl solution 0.2 ml 0.17 M NaOH 1.6 ml Collagen R solution Mix 2. Coat Petri dish with the mixture evenly. 3. Place it in the incubator for at least 1 hour at 37 °C. 4. Aspirate excess fluid and wash 2x with e.g. PBS, pH 7.0. Cells can now be seeded. |

Floating collagen membranes:

After sowing of the cells in the collagen layer, the collagen membrane can be removed from the bottom with a sterile spatula under circle movement of the culture dish and will then float in the medium as membrane.

Literature:

1. Iota, L. A. et al. (1978) Nature 272, 622-624
2. Kleinmann, K. et al (1981) J. Cell Biol. 88, 473-485
3. Grinnell F., & Benett, M. H. (1981) J. Cell Sci. 48, 19-34
4. Rubin, K. et al (1981) Cell 24, 463-470
5. Grinnell, F. (1982), J. Cell Sci. 58, 95-108
6. Dunn, G. A. & Ebendal, T. (1978) Exptl. Cell Res. 11, 475-479
7. Bellows, C. G. et al (1982) J. Ultrastructure Res. 78, 178-192
8. Harris, A. K. et al (1981) Nature 290, 249-251
9. Michaelopoulos, G. & Pitot, H. C. (1975) Exptl. Cell. Res. 94, 70-78
10. Richards, J. et al (1982) Exptl. Cell Res. 141, 433-443
11. Iwig, M. et al (1982) Exptl. Cell Res. 131, 47-55
12. Bell, E. et al. (1979) Proc. Natl. Acad. Sci. USA 76, 1274-1278

Ver 0922